

Partie contractuelle														
Valeurs spécifiées sur lesquelles le producteur s'engage														
Classe granulaire		Norme										Catégorie		
4 10		Norme NF P 18-545 Article 10										Code A		
	2	4	5.6	7.1	8	10	12.5	14	16	20	f	FI	LA	WA24
V.S.S.+U	6.0	20.0				100.0		100.0		100.0	4.60	24.0	33	3.0
V.S.S.	5.0	15.0				95.0		100.0		100.0	4.00	20.0	30	2.5
V.S.I.	0.0	0.0				80.0		98.0		100.0				
V.S.I.-U	0.0	0.0				75.0		97.0		100.0				
Ecart-type max														

Partie informative														
Résultats de production														
du 01/08/16 au 26/12/16														
	2	4	5.6	7.1	8	10	12.5	14	16	20	f	FI	LA	WA24
Maximum	3.8	4.0	7.4	26.3	51.4	91.2	100.0	100.0	100.0	100.0	2.29		26	1.2
Xf+1.25xEcart-types	3.2	3.5	5.0	23.3	49.9	91.4	100.0	100.0	100.0	100.0	2.25		26	1.2
Moyenne Xf	2.4	2.6	3.3	17.7	41.8	86.3	99.5	99.9	100.0	100.0	1.82	3.9	24	1.1
Xf-1.25xEcart-types	1.6	1.7	1.6	12.1	33.6	81.2	98.9	99.7	99.9	100.0	1.39		22	1.1
Minimum	1.6	1.7	1.9	9.3	26.6	77.6	98.5	99.5	99.7	100.0	1.29		22	1.1
Ecart-type	0.64	0.73	1.37	4.47	6.52	4.05	0.48	0.15	0.08	0.00	0.340		1.0	0.00
Nombre de résultats	18	18	18	18	18	18	18	18	18	18	18	1	5	5
Norme											NF EN 933-1	NF EN 933-3	NF EN 1097-2	EN 12004 art 5.4 mod 3
Dernier	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	26/12/2016	16/08/2016	12/10/2016	27/04/2016

